

MATERIAL

ESTE CREAM TRAVERTINE

VEIN CUT

ASTM C-880

FLEXURAL STRENGTH

AVERAGE PERPENDICULAR MODE

77.0 Kgs/Sqcm

7.55 Mpa

1.095 Psi 623.04 Psi

AVERAGE PARALLEL MODE

43.8 Kgs/Sqcm

4.29 Mpa

ASTM C-170

COMPRESSIVE STRENGTH

AVERAGE PERPENDICULAR MODE

448.2 Kgs/Sqcm

43.95 Mpa

6375.53 Psi

AVERAGE PARALLEL MODE

680.1 Kgs/Sqcm

66.69 Mpa

9674.25 Psi

ASTM C-97

ABSORPTION AND BULK SPECIFIC GRAVITY

DENSITY

2456.5 Cbmt/Kgs

153.35 CbR/Lbs

ABSORPTION

1.14%